FUELZON
Oil & Gas

BITUMEN PENETRATION

GRADE-60/70

Uses: This grade is primarily used to pave roads in mild area due to its medium air blowing..

SPECIFICATIONS

CHARACTERESTIC	RESULT	TEST METHOD
Specific Gravity @ 25/25 °C	1.01/1.06	ASTM D -70
Penetration@ 25 °C	60/70	ASTM D -5
Softening point °C	49/56	ASTM D -36
Ductility @ 25 °C	100min	ASTM D -113
Loss of Heating	0.2max	ASTM D -6
Drop in penetration after heating	20%max	ASTM D -6 & D -5
Flash point °C	250 min	ASTM D -92
Solubility in CS2(%wt.)	99.5 min	ASTM D -4
Organic Matter insoluble in Cs2(w)%	--	ASTM D -4
Spot Test	Negative	A.A.S.H.O.

P2-Hamriyah Business Centre, Hamriyah
Freezone Sharjah, United Arab Emirates
Email:info@fuelzon.com
Web: www.fuelzon.com
Tel:+971 588146787