CUTBACK BITUMEN MC-250

Medium Curing , Contains 67% bitumen

BITUMEN APPLICATIONS:

Sand Seal

Prime Coat (Open and Tight Surface)

SPECIFICATIONS

PROPERTIES	MIN	MAX	TEST METHOD
Kinematic Viscosity at 60 ° C mm2/s	250	500	ASTM -D2170
Flash point {Tag open-cup),°C	66	-	ASTM -D3143
Distillate Test: **Distillate test, volume percent of total distillate to 360°C:**			
To 225 ° C	-	10	ASTM -D402
To 260° C	15	55	ASTM -D402
To 316 ° C	60	87	ASTM -D402
Residue from distillation to 360 ° C: Percent volume by difference	67	-	ASTM -D402
Test on residue from distillation:			
Viscosity at 60 °C	30	120	ASTM -D2170
Penetration at 25 °C	120	250	ASTM -D5
Ductility at 25 °C	100	-	ASTM -D113
Solubility in trichloroethylene,%	99	-	ASTM -D2042
Water ,%	-	0.2	ASTM -D95