

RUBBER PROCESS OIL

Aromatic

PRODUCT CODE: SP-RPO-1		
CHARACTERISTIC	RESULT	TEST METHOD -ASTM
Kinematic viscosity @ 100 °C	40-70	D-445
Flashpoint (° C) min	235	D-92
Aniline point	27-37	D611-IP2

PRODUCT CODE: SP-RPO-2		
CHARACTERISTIC	RESULT	TEST METHOD-ASTM
Kinematic Viscosity @ 100 °C	40-60	D-445
Density @15.6 °C (g/cm ³) typical)	1.02	D-4052
Flash Point °C min	235	D-92
Aniline Point °C	25-37	D-611
Sulphated Ash %wt max	0.02	D-874
Pour Point °C	+24	D-97
Sulfur Content -% wt/ typical	4.1	D-4951- D-5185