

RUBBER PROCESS OIL

NAPHTHENIC OIL

PRODUCT CODE: NAP-100		
TEST	METHOD	TYPICAL
Aniline Point, °C	D-611	86
Color, Astm	D-1500	L1
Flash Point, Coc, °C	D-92	195
Pour Point, °C	D-97	-30
Density@15°C , Kg/Dm3	D-4052	0.9180
VISCOSITY @40°C, Cst	D-445	98.00
Sulfur, Wt%	D-2622	0.05