

RUBBER PROCESS OIL

NAPTHENIC OIL

PRODUCT CODE: NAP-400		
TEST	METHOD	TYPICAL
Aniline Point, °C	D-611	73
Color	D-1500	L3.0
Flash Point, Coc, °C	D-92	227
Pour Point, °C	D-97	-1
Specific Gravity, 15.6 °C	D-1298	0.9446
Viscosity, Cst	D-445	
@ 100°C		13.93
@ 40°C		349.5
Refractive Index @ 20°C	D-1218	1.5229
Sulfur, Wt%	D-2622	0.55